



Thermal Ceramics high temperature insulating firebrick are produced with unique processes. The bond developed is a ceramic bond that is formed by high temperature firing. This produces bricks that are very stable and strong at temperatures higher than 2600°F (1427°C).

Features

- High temperature insulating firebrick with use limits up to 3250°F (1788°C)
- Excellent strength and thermal stability
- Low heat storage
- High purity
- Excellent thermal conductivity

Applications

- Atmosphere furnace
- Forge furnaces
- Ethylene furnace sidewalls
- Ceramic kilns
- High temperature back-up insulation
- Carbon baking furnaces
- High temperature kiln linings
- Removable furnace doors

Physical Characteristics

Standard sizes* 9" x 4½" x 2½" and 9" x 4½" x 3"
(22.5 cm x 11.25 cm x 6.25 cm and
22.5 cm x 11.25 cm x 7.5 cm)

* Special sizes available upon request.

High Temperature Insulating Firebrick

Product Information

Physical properties	TC-26	K-26	JM-26	JM-28	JM-30	Insalcor
Recommended Hot Face use limit, °F	2600	2600	2600	2800	3000	3250
°C	(1427)	(1427)	(1427)	(1538)	(1649)	(1788)
Density, nominal						
lb/9" straight (kg)	2.8 (1.2)	2.3 (1.04)	2.9 (1.3)	3.2 (1.45)	3.8 (1.72)	4.6 (2.09)
pcf (kg/m ³)	48 (769)	40 (641)	50 (801)	55 (881)	65 (1041)	82 (1314)
Modulus of rupture, psi (Mpa)	200 (1.37)	145 (1)	190 (1.31)	220 (1.51)	250 (1.72)	450 (3.1)
Cold crushing strength, psi (Mpa)	270 (1.86)	245 (1.7)	290 (2)	340 (2.35)	440 (3.03)	900 (6.2)
Permanent linear shrinkage, % , after 24 hours						
@ 2550°F (1400°C)	-0.1	-0.1	-0.2	-	-	-
@ 2750°F (1510°C)	-	-	-	-0.7	-	-
@ 2950°F (1620°C)	-	-	-	-	-0.7	-
@ 3150°F (1732°C)	-	-	-	-	-	+0.4
Deformation under hot load, % @ 10 psi (0.07 Mpa)						
1½ hours @ 2200°F (1204°C)	-0.2	-0.2	-0.2	-0.1	-	-
1½ hours @ 2400°F (1315°C)	-	-	-	-	-0.3	-
1½ hours @ 2640°F (1448°C)	-	-	-	-	-	+0.1

Chemical Composition

Alumina, Al ₂ O ₃	47	48	60.4	67	69.9	77
Silica, SiO ₂	48.6	38	36.1	30.5	28.1	21.5
Ferric oxide, Fe ₂ O ₃	0.7	0.4	0.4	0.3	0.3	0.4
Titanium oxide, TiO ₂	1.3	0.9	1.0	0.9	1.2	0.6
Calcium oxide, CaO	0.3	12.3	0.1	0.3	0.2	0.1
Magnesium oxide, MgO	0.1	0.1	0.2	-	0.1	0.1
Alkalies, as Na ₂ O and K ₂ O	2.0	0.3	1.8	1.0	0.2	0.3

Thermal Conductivity, BTU•in./hr•ft²•°F (W/m•k) ASTM C 201

Mean temperature	TC-26	K-26	JM-26	JM-28	JM-30	Insalcor
@ 500°F (260°C)	1.6 (0.23)	1.16 (0.17)	1.8 (0.26)	2.3 (0.33)	2.8 (0.40)	5.5 (0.79)
@ 1000°F (538°C)	1.9 (0.27)	1.34 (0.19)	2.0 (0.29)	2.4 (0.34)	2.9 (0.42)	5.6 (0.80)
@ 1500°F (815°C)	2.2 (0.32)	1.52 (0.22)	2.1 (0.30)	2.6 (0.37)	3.1 (0.45)	6.3 (0.91)
@ 2000°F (1093°C)	2.6 (0.37)	1.74 (0.25)	2.3 (0.33)	2.7 (0.39)	3.3 (0.47)	7.6 (1.09)
@ 2500°F (1371°C)	-	-	-	-	-	9.2 (1.33)

The values given herein are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Thermal Ceramics office to obtain current information.

Thermal Ceramics is a trademark of The Morgan Crucible Company plc. K, TC, JM, and insalcor are trademarks of Thermal Ceramics.

Marketing Communications Offices North America - Sales Offices

Thermal Ceramics Americas

T: (706) 796 4200
F: (706) 796 4398

Thermal Ceramics Asia Pacific

T: +65 6733 8068
F: +65 6733 3498

Thermal Ceramics Europe

T: +44 (0) 151 334 4030
F: +44 (0) 151 334 1684

Canada

T: +1 (905) 335 3414
F: +1 (905) 335 5145

Mexico

T: +52 (555) 576 6622
F: +52 (555) 576 3060

United States of America

Southeastern Region
T: (800) 338 9284
F: (706) 796 4324

Midwest Region

T: (866) 785 2738
F: (866) 785 2760

Eastern Region

T: (866) 785 2763
F: (866) 785 2764

Western Region

T: (866) 785 2765
F: (866) 785 2782

South America - Sales Offices

Argentina

T: +54 (11) 4373 4439
F: +54 (11) 4372 3331

Brazil

T: +55 (21) 2418 1366
F: +55 (21) 2418 1205

Chile

T: +56 (2) 854 1064
F: +56 (2) 854 1952

Colombia

T: +57 (2) 2282935/2282803/2282799
F: +57 (2)

2282935/2282803/23722085

Guatemala

T: +50 (2) 4733 295/6
F: +50 (2) 4730 601

Venezuela

T: +58 (241) 878 3164
F: +58 (241) 878 6712